

Amendments to the Claims:

This listing of claims will replace all prior versions, and listings, of claims in the application:

1. (canceled)
2. (currently amended) ~~The golf ball of claim 1;~~ A golf ball comprising:
an inner core having a compression of less than about 65;
at least one outer core layer surrounding the inner core having a specific gravity greater
than or equal to a specific gravity of the inner core; and
a cover surrounding the outer core layer;
wherein the inner core hardness is about 78 Shore C and the outer core hardness is greater than about 90 Shore C; and
wherein the inner core has a diameter of from about 1.4 inches to about 1.5 inches and
the outer core has a thickness of from about 0.05 inches up to about 0.1 inches.
- 3-9. (canceled)
10. (currently amended) The golf ball of claim 1 2, wherein the cover layer comprises polyurea or polyurethane.
11. (currently amended) The golf ball of claim 1 2, further comprising a moisture barrier layer disposed between the outer core layer and the cover layer, wherein the moisture barrier layer comprises a moisture vapor transmission rate that is less than a moisture vapor transmission rate of the cover layer.
12. (original) The golf ball of claim 11, wherein the moisture barrier layer has a specific gravity of from about 1 to about 2, and a thickness of less than about 0.03 inches.
13. (original) The golf ball of claim 11, wherein the moisture barrier layer comprises a styrene block copolymer and aluminum flake.

14-22. (canceled)

23. (original) A golf ball comprising:

a multi-layer core comprising:

an inner core having a Shore C hardness less than about 80 and a compression of less than about 70; and

at least one outer core layer having a Shore C hardness of greater than about 80,

an amount of zinc diacrylate of greater than about 35 pph; and

a cover layer having a Shore D hardness of less than about 65;

wherein at least one outer core layer has a moisture vapor transmission rate that is lower than that of the cover layer, and the multi-layer core has a diameter of greater than about 1.58 inches.

24. (original) The golf ball of claim 23, wherein the outer core layer has a Shore C hardness of greater than about 90.

25. (original) The golf ball of claim 24, wherein the zinc diacrylate level in the outer core layer is greater than about 40 pph.

26. (original) The golf ball of claim 24, wherein the multi-layer core diameter is greater than about 1.6 inches.

27. (original) The golf ball of claim 24, wherein the inner core comprises about 100 pph of a polybutadiene rubber, greater than about 25 pph of a zinc diacrylate, greater than about 0.5 pph of an organic peroxide and a sufficient amount of filler to produce the inner core specific gravity, the outer core comprises about 100 pph of a polybutadiene rubber, greater than about 0.6 pph of an organic peroxide, a sufficient amount of filler to produce the outer core specific gravity, and the cover layer comprises polyurea or polyurethane.

28. (canceled)

29. (canceled)
30. (previously presented) A golf ball comprising:
an inner core having a compression of less than about 65;
at least one outer core layer surrounding the inner core and having a hardness of at least 80 Shore C and a specific gravity greater than or equal to a specific gravity of the inner core; and
a cover surrounding the outer core layer;
wherein the inner core has a hardness less than a hardness of the outer core, and
wherein the cover layer comprises polyurea or polyurethane.
31. (previously presented) The golf ball of claim 30, wherein the inner core has a diameter of from about 1.4 inches to about 1.5 inches and the outer core has a thickness of from about 0.05 inches up to about 0.1 inches.
32. (previously presented) The golf ball of claim 30, wherein the cover layer has a thickness of from about 0.03 inches to about 0.04 inches.
33. (previously presented) The golf ball of claim 30, wherein the inner core has a compression of less than about 50.
34. (previously presented) The golf ball of claim 30, wherein the outer core layer has a specific gravity of at least 1.1.
35. (previously presented) The golf ball of claim 30, wherein the golf ball further comprises a moisture barrier layer disposed between the outer core layer and the cover layer, wherein the moisture barrier layer comprises a moisture vapor transmission rate that is less than a moisture vapor transmission rate of the cover layer.

36. (previously presented) The golf ball of claim 35, wherein the moisture barrier layer has a specific gravity of from about 1 to about 2.

37. (previously presented) The golf ball of claim 36, wherein the moisture barrier layer has a thickness of less than about 0.03 inches.

38. (previously presented) The golf ball of claim 35, wherein the moisture barrier layer comprises a styrene block copolymer and aluminum flake.